

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
26 April 2001 (26.04.2001)

PCT

(10) International Publication Number
WO 01/29919 A1

(51) International Patent Classification⁷: H01M 6/04,
10/26, 6/18, 4/58, 4/36, 4/58, 4/88, C01G 37/14

Gan (IL). GIZBAR, Chaim [IL/IL]; 2 Hasmadar St.,
75491 Rishon Lezion (IL).

(21) International Application Number: PCT/US00/28683

(74) Common Representative: FRIEDMAN, Mark, M.; c/o
Castorina, Anthony, Suite 207, 2001 Jefferson Davis High-
way, Arlington, VA 22202 (US).

(22) International Filing Date: 17 October 2000 (17.10.2000)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
09/419,940 18 October 1999 (18.10.1999) US

(81) Designated States (*national*): AE, AL, AM, AT, AU, AZ,
BA, BB, BG, BR, BY, CA, CH, CN, CR, CU, CZ, DE, DK,
DM, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL,
IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU,
LV, MA, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT,
RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA,
UG, US, UZ, VN, YU, ZA, ZW.

(71) Applicant (*for all designated States except US*): BAR-
ILAN UNIVERSITY [IL/IL]; 52900 Ramat Gan (IL).

(84) Designated States (*regional*): ARIPO patent (GH, GM,
KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian
patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European
patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE,
IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG,
CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).

(71) Applicant (*for TJ only*): FRIEDMAN, Mark, M.
[US/IL]; 1 Alharizi St., 43406 Raanana (IL).

(72) Inventors; and

(75) Inventors/Applicants (*for US only*): AURBACH, Doron
[IL/IL]; 62 Uziel St., 51646 Bnei Brak (IL). GOFER,
Yosef [IL/IL]; 11/3 Haoranim St., 45263 Hod Hasharon
(IL). SCHECHTER, Alexander [IL/IL]; 32 Tamar St.,
60190 Neve Monoson (IL). ZHONGHUA, Lu [IL/IL];
Dept. of Chemistry, Bar-Ilan University, 52900 Ramat

Published:

— With international search report.

For two-letter codes and other abbreviations, refer to the "Guid-
ance Notes on Codes and Abbreviations" appearing at the begin-
ning of each regular issue of the PCT Gazette.

WO 01/29919 A1

(54) Title: HIGH-ENERGY, RECHARGEABLE, ELECTROCHEMICAL CELLS NON-AQUEOUS ELECTROLYTES

(57) Abstract: The present invention provides a non-aqueous electrolyte for use in an electrochemical cell comprising: (a) at least one organic solvent; (b) at least one electrolytically active salt represented by the formula: $M'^{+m}(ZR_nX_{q-n})_m$ in which: M' is selected from a group consisting of magnesium, calcium, aluminum, lithium and sodium; Z is selected from a group consisting of aluminum, boron, phosphorus, antimony and arsenic; R represents radical selected from the following groups: alkyl, alkenyl, aryl, phenyl, benzyl, and amido; X is a halogen (I, Br, Cl, F); $m=1-3$; and $n=0-5$ and $q=6$ in the case of Z=phosphorus, antimony and arsenic, and $n=0-3$ and $q=4$ in the case of Z=aluminum and boron. Rechargeable, high energy density electrochemical cells containing an intercalation cathode, a metal anode, and an electrolyte of the above-described type are also disclosed.

BEST AVAILABLE COPY

HIGH-ENERGY, RECHARGEABLE, ELECTROCHEMICAL CELLS NON-AQUEOUS ELECTROLYTES

FIELD AND BACKGROUND OF THE INVENTION

The present invention relates to electrochemical cells utilizing a
5 non-aqueous liquid electrolyte with an intercalation cathode, and more
particularly, to electrochemical cells utilizing a non-aqueous liquid electrolytic
solution, an intercalation cathode and a magnesium anode.

Rechargeable, high energy density electrochemical cells of various kinds
are known. Such cells usually consist of a transition metal oxide or
10 chalcogenide cathode-active material, an anode-active alkali metal or alkali
metal intercalation compound, and an electrolytic solution containing a
dissolved alkali-based salt in an aprotic organic or inorganic solvent or
polymer.

Theoretically, a rechargeable cell is capable of charging and discharging
15 indefinitely, however, in practice such performance is unattainable. The
degradation mechanisms of the various anodes, cathodes and electrolytes are
complex and are reviewed in the general literature.

Two basic types of cathodes are appropriate for a battery system that is
rechargeable at ambient temperatures. A liquid cathode can be used, allowing
20 reactions to take place with facility. Liquid cathodes are also advantageous in
that thin films or crusts forming on the surface of the cathode tend to crack,
such that the cathode activity remains high over the course of the cycling. The
mobility of the cathodic material is a liability, however, in that contact with the
anode short-circuits the cell. Thus, an electrochemical cell with a liquid
25 cathode requires protective, insulating films on the anode.

A solid cathode must be insoluble in the electrolyte, and must be able to
receive and release a charge-compensating ion in a substantially reversible and
fast manner. A prime example of a solid cathode of this variety is an

intercalation cathode. Intercalation chemistry focuses on the insertion of ions or neutral molecules into an inorganic or organic matrix. In a typical intercalation cathode, cations dissolved in the electrolytic solution are inserted into the inorganic matrix structure.

- 5 One type of intercalation materials of particular importance is known as Chevrel-phase material, or Chevrel compounds. Chevrel compounds contain an invariant portion consisting of molybdenum and a chalcogen – sulfur, selenium, tellurium, or mixtures thereof. The invariant portion is generally of the formula Mo_6T_n , where T represents the chalcogen and n is usually about 8.
- 10 The unique crystal structure of Chevrel-phase materials allows the insertion of one or more metal ions in a reversible, partially-reversible, or irreversible fashion. The stoichiometry of the intercalation compound can be represented as $\text{M}_x\text{Mo}_6\text{T}_n$, where M represents the intercalated metal and x may vary from 0 (no intercalated metal) to 4 or less, depending on the properties of the particular
- 15 metal.

 The intercalation of metal ions into the Chevrel compound releases energy. Since the process is partially or fully reversible, these compounds are particularly suitable as electrodes in electrochemical cells. For example, lithium, the predominant intercalation ion, can be removed from the Chevrel

20 compound by the application of electrical energy. The energy is released as electrical energy upon reintercalation.


- The cathode-active material in the high energy density, rechargeable electrochemical cells must be paired with a suitable anode-active material, which is most commonly made of an active metal such as alkali metals.
- 25 However, the performance of a particular anode-cathode couple is strongly influenced by the nature of the electrolyte system. Certain non-aqueous electrolytes are known to perform well with a particular anode-cathode couple and be ineffective or significantly less effective with other anode-cathode couples, because of reaction between the components causes degradation over
- 30 time. As a result, much of the prior art relates to the cathode-active material, the anode-active material and the electrolyte not only as independent entities,

but also as units within an appropriate battery system.

U.S. Patent No. 4,104,451 to Klemann et al. discloses reversible batteries with an alkali metal anode, a chalcogenide cathode, and organometallic alkali metal salts in organic solvents as the electrolyte system.

- 5 Non-aqueous electrolyte systems containing alkali metal salts of organic boron-based or aluminum-based anions are disclosed.

Organoborate salts of alkali metals represented by the formula



15


are disclosed in U.S. Patent No. 4,511,642 to Higashi et al., wherein R1-R4 are organic radicals selected from the following groups: alkyl, aryl, alkenyl, cycloalkyl, allyl, heterocyclic, and cyano, and M⁺ represents an alkali metal ion.

20

U.S. Patent No. 4,139,681 describes cells containing electrolytically active metal salt complexes having the formula ZMR_nX_i, wherein Z is a metal from a group containing aluminum, the Rs are specified haloorganic radicals, the Xs are selected from various halides, alkyls, aryls, alkaryls and aralkyls. M is specified to be an alkali metal, with lithium being the preferred embodiment.

25

U.S. Patent No. 4,542,081 to Armand et al. describes solutions for the constitution of solid electrolyte materials of electrochemical generators. The compound is of the formula



30

in which Z is a trivalent element capable of entering into 4-coordination, such


as aluminum, and R represents groups which are non-proton donors. M is specified to be an alkali metal.

The prior art described above, including U.S. Patent Nos. 4,104,451, 4,511,642, 4,139,681 and 4,542,081, specifies that M is an alkali metal. The use of an alkaline earth metal anode such as magnesium would appear disadvantageous relative to the use of an alkali metal such as lithium because alkali metal anodes are much more readily ionized than are alkaline earth metal anodes. In addition, on recharge the cell must be capable of re-depositing the anode metal that was dissolved during discharge, in a relatively pure state, and without the formation of deposits on the electrodes.

However, there are numerous disadvantages to alkali batteries. Alkali metals, and lithium in particular, are expensive. Alkali metals are highly reactive. Alkali metals are also highly flammable, and fire due to the reaction of alkali metals with oxygen or other active materials is extremely difficult to extinguish. Lithium is poisonous and compounds thereof are known for their severe physiological effects, even in minute quantities. As a result, the use of alkali metals requires specialized facilities, such as dry rooms, specialized equipment and specialized procedures.


In contradistinction, magnesium metal and aluminum metal are easy to process. The metals are reactive, but undergo rapid passivation of the surface, such that the metals are highly stable. Both magnesium and aluminum are inexpensive relative to the alkali metals.

U.S. Patent No. 4,894,302 to Hoffman et al. discloses an electrochemical cell having an intercalation cathode, an alkaline earth anode, and a non-aqueous liquid electrolyte containing an organic solvent and an electrolytically active, organometallic alkaline earth metal salt represented by the formula



wherein Z is boron or aluminum; R1-R4 are radicals selected from the following groups: alkyl, aryl, alkaryl, aralkyl, alkenyl, cycloalkyl, allyl, heterocyclic alkyl, and cyano; and M represents an alkaline earth metal such as magnesium. The radicals can be inertly substituted with substituents that have no detrimental effect upon the electrolytic properties of the electrolyte composition with respect to effectiveness in an electrochemical cell, such as halogenated or partially halogenated derivatives of the above groups. While exhaustive care is taken to disclose a broad range of organic radicals and halogenated organic radicals, bonding the metallic species of the anion (Z) to another inorganic species is not considered.

U.S. Patent No. 5,491,039 describes a solid, single-phase electrolyte containing a solid polymeric matrix and an organometallic ion salt represented by the formula



wherein Z is boron, aluminum or titanium; Rs are various substituted or unsubstituted organic radicals; M is lithium, sodium, potassium, or magnesium, c is 1 or 2, and n is an integer from 1 to 6. As in U.S. Patent No. 4,894,302, a broad range of organic radicals and halogenated organic is disclosed, but bonding the metallic species of the anion (Z) to another inorganic species is not reported.

Both U.S. Patent No. 5,491,039 and U.S. Patent No. 4,894,302 disclose electrochemical cells having an alkaline earth anode such as magnesium. For


commercial application, however, such magnesium batteries must be essentially rechargeable and must have a reasonable shelf life. Sustaining a voltage of 1.5 volts is problematic or impossible with the usual intercalation cathodes and electrolytes according to prior art. Magnesium batteries operating
5 at 1.5 volts are particularly prone to electrolyte decomposition and to encrustation/passivation of both electrode surfaces.

Thus, there is a widely recognized need for, and it would be highly advantageous to have, an improved non-aqueous electrolyte that allows the production of a practical, rechargeable magnesium battery which would be
10 safer and cleaner, and more durable, efficient and economical than heretofore known.

SUMMARY OF THE INVENTION

The present invention is a new type of electrolyte for use in electrochemical cells. The properties of the electrolyte include high
15 conductivity and an electrochemical window that can exceed 2V vs. Mg/Mg^{+2} . The use of the electrolyte in an appropriate cell promotes the substantially-reversible deposition of the intercalating metal.

According to the teachings of the present invention there is provided a non-aqueous electrolyte for use in an electrochemical cell, said electrolyte
20 comprising: (a) at least one organic solvent; (b) at least one electrolytically active salt represented by the formula:



in which: M' is selected from a group consisting of magnesium, calcium, aluminum, lithium and sodium; Z is selected from a group consisting of
25 aluminum, boron, phosphorus, antimony and arsenic; R represents radicals selected from the following groups: alkyl, alkenyl, aryl, phenyl, benzyl, and amido; X is a halogen (I, Br, Cl, F); $m = 1-3$; and $n = 0-5$ and $q = 6$ in the case of $Z = \text{phosphorus, antimony and arsenic}$, and $n = 0-3$ and $q = 4$ in the case of

Z = aluminum and boron.

According to further features in preferred embodiments of the invention described below, the electrolyte according to the present invention is incorporated into specific electrochemical cells comprised of said electrolyte and an appropriate anode-cathode pair.

According to further features in the preferred embodiments, one such appropriate anode-cathode pair is a magnesium metal anode and a magnesium insertion-compound cathode.

In yet another preferred embodiment, the magnesium insertion-compound cathode is a magnesium-Chevrel intercalation cathode of the form



wherein $x = 0 - 1$ and $y = 0 - 2$.

The present invention successfully addresses the shortcomings of the presently-known electrolytes and provides the basis for the production of a viable, rechargeable magnesium battery with a nominal voltage exceeding 1.5 volts.

BRIEF DESCRIPTION OF THE DRAWINGS

The invention is herein described, by way of example only, with reference to the accompanying drawings, wherein:

FIG. 1a and FIG. 1b are graphs displaying typical cyclic voltammograms of magnesium salts solutions in tetrahydrofuran (THF) using a gold electrode;

FIGS. 2a-2d are Scanning Electron Microscope (SEM) micrographs showing different forms of metallic magnesium deposition on a copper electrode; and

FIG. 3 is a graph of the voltage patterns of an electrochemical cell consisting of a Chevrel-phase cathode, magnesium metal anode, and an

electrolyte containing $\text{Mg}(\text{AlCl}_2\text{BuEt})_2$ salt in THF, in which cycles 340-345 are plotted next to the first five cycles (cycles 1-5).

DESCRIPTION OF THE PREFERRED EMBODIMENTS

5 The present invention is a new type of electrolyte for use in electrochemical cells. The properties of the electrolyte include high conductivity and an electrochemical window that can exceed 2V vs. Mg/Mg^{+2} . The use of the electrolyte in an appropriate cell promotes the substantially-reversible deposition of magnesium metal on the anode current collector and the reversible intercalation of magnesium in the cathode material.

10 Although alkali metals are readily ionized, the use of other metal anodes, such as magnesium or aluminum has decided advantages. Magnesium and aluminum are very inexpensive relative to alkali metals. Alkali metals are highly reactive and highly flammable, and alkali fire is extremely difficult to extinguish. Lithium in particular is poisonous and compounds thereof are
15 known for their severe physiological effects, even in minute quantities. As a result, the use of alkali metals requires specialized facilities, such as dry rooms, specialized equipment and specialized procedures.

Magnesium and aluminum are reactive, but undergo rapid passivation of the surface, such that for all practical purposes, the metals are highly stable.
20 Magnesium and aluminum are available and inexpensive, non-toxic, non-hazardous, and easy to work with, and as such, are highly-desirable raw materials for electrochemical cells and for electrolytic solutions in particular.

Although primary electrochemical cells based on magnesium are known, such cells are non-rechargeable and are used solely for military applications.
25 Sustaining a voltage of 1.5 volts is problematic or impossible with the usual intercalation cathodes and electrolytes according to prior art. Magnesium batteries operating at 1.5 volts are particularly prone to electrolyte decomposition and to encrustation/passivation of the electrode surface.

The present invention provides a non-aqueous electrolyte for use in an electrochemical cell comprising: (a) at least one organic solvent; (b) at least one electrolytically active salt represented by the formula:



5 in which: M' is selected from a group consisting of magnesium, calcium, aluminum, lithium and sodium; Z is selected from a group consisting of aluminum, boron, phosphorus, antimony and arsenic; R represents radical selected from the following groups: alkyl, alkenyl, aryl, phenyl, benzyl, and amido; X is a halogen (I, Br, Cl, F); m = 1-3; and n = 0-5 and q = 6 in the case
10 of Z = phosphorus, antimony and arsenic, and n = 0-3 and q = 4 in the case of Z = aluminum and boron.

As described above, the electrochemical window of a cell with an electrolyte according to the present invention and an appropriate anode-cathode pair is 2 volts, such that the cell can be operated in a stable, reversible fashion
15 at 1.5 volts without decomposition of the electrolyte and encrustation of the electrodes.

In a preferred embodiment of the invention, the electrolyte according to the present invention functions in an electrochemical cell with a metal anode and an intercalation cathode.

20 Certain non-aqueous electrolytes are known to perform well with a particular anode-cathode couple and be ineffective or significantly less effective with other anode-cathode couples, either because the electrolyte is not inert or because it degrades during cycling. It is relevant, therefore, to treat the electrolyte, not only as an independent entity, but also as a unit within a system
25 containing an appropriate anode-cathode pair.

Hence, according to further features in preferred embodiments of the invention described below, the electrolyte according to the present invention is incorporated into specific electrochemical cells containing an appropriate anode-cathode pair.

30 While various metals are suitable as anodes for the electrolytic solution,

including magnesium, lithium, aluminum and calcium, a particularly appropriate battery includes the electrolyte according to the present invention, a magnesium metal anode and a magnesium insertion compound cathode.

In yet another preferred embodiment, the magnesium
5 insertion-compound cathode is a magnesium-Chevrel intercalation cathode of the form



wherein $x = 0-1$ and $y = 0-2$.

The principles and operation of an electrolytic cell with an improved
10 electrolyte according to the present invention may be better understood with reference to the drawings and the accompanying description.

The electrolyte composition of the present invention includes an organic solvent and electrochemically-active organometallic salts of the form
15 $\text{M}'^{+m}(\text{ZR}_n\text{X}_{q-n})_m$, as described above. Organometallic salts of this form may be combined with compatible non-organometallic salts or with compatible organometallic salts of other forms.

Many and diverse organic solvents are suitable for use in the electrolyte of the present invention, including ethers, organic carbonates, lactones, ketones,
20 nitriles, aliphatic and aromatic hydrocarbon solvents and organic nitro solvents. More specifically, suitable solvents include acetonitrile, hexane, toluene, THF, diglyme, triglyme, tetraglyme, dimethoxyethane, diethoxyethane, diethylether, dimethoxyethane, dimethylsulfoxide, dimethylsulfite, sulfolane, and nitromethane.

25 Intercalation cathodes used in conjunction with the electrolyte according to the present invention include transition metal oxides, chalcogenides and halogenides and combinations thereof. More specifically, the transition metal oxides include V_2O_5 , TiS_2 , MoS_2 , ZrS_2 , Co_3O_4 , MnO_2 , Mn_2O_4 , and the chalcogenides include Chevrel-phase compounds.

EXAMPLE 1


A magnesium-Chevrel intercalation cathode for use in conjunction with the electrolyte according to the present invention was synthesized according to the procedure developed by Goecke, Sch?lhorn et al. (Inorg. Chem. 26, p. 1805 (1987)). Elemental sulfur, molybdenum and copper of high purity were added in a stoichiometric ratio of 4:3:1. After intimate mixing and pressing into pellets, the mixture was sealed in a quartz ampoule under a vacuum of 10^{-5} Torr. The ampoule was placed in a furnace, and the temperature was raised at a rate of $400^{\circ}\text{C}/\text{h}$ to 450°C . The temperature was maintained at 450°C for 24 hours. Again, the temperature was raised at a rate of $400^{\circ}\text{C}/\text{h}$ to 700°C and was maintained at 700°C for 24 hours. The temperature was then raised at a rate of $120^{\circ}\text{C}/\text{h}$ to 1050°C and was maintained at 1050°C for 48 hours. After cooling to room temperature at a rate of $120^{\circ}\text{C}/\text{h}$, the ampoule was broken open. The copper molybdenum sulfide ($\text{Cu}_2\text{Mo}_6\text{S}_8$) obtained was milled into fine powder using mortar and pestle.

The copper molybdenum sulfide powder was mixed with Teflon-loaded carbon black (CB). The resulting paste was spread on stainless steel mesh and pressed. The composite electrode formed was dried under vacuum at room temperature for 24 hours.

The electrode was subsequently subjected to electrochemical pretreatment in which some of the copper ions in the host matrix ($\text{Cu}_2\text{Mo}_6\text{S}_8$) were deinserted. The electrochemical deintercalation of copper was performed in a non-aqueous medium, a 1M solution of $\text{Mg}(\text{ClO}_4)_2$ in acetonitrile. The deinsertion was performed by a galvanostatic charging process in which the upper limit of the potential was controlled.

After thorough washing in acetonitrile and subsequent drying of the electrode, charging-discharging cycles were conducted in a 1M solution of $\text{Mg}(\text{ClO}_4)_2$ in acetonitrile at various scan rates between -1.6V and 0.01 V, relative to the Ag/Ag^{+1} reference electrode. A pronounced electrochemical redox activity was observed, with a main oxidation peak at -1.219 V vs.

Ag/Ag⁺ and a corresponding main reduction peak at -1.41 V vs. Ag/Ag⁺. The charge associated with the intercalation-deintercalation process was 71mAh/g and 72mAh/g, respectively, which correspond to $y = 1.09-1.12$ in the formula



- 5 The chemical and electrochemical reversibility of the intercalation process was demonstrated over multiple cycles.

EXAMPLE 2

- 10 Referring now to the drawings, FIG. 1a and FIG. 1b are graphs displaying typical cyclic voltammograms of ether-magnesium organo-halo-aluminates solutions in tetrahydrofuran (THF) using a gold electrode.

- FIG. 1a shows the potentiodynamic behavior of $\text{Mg}(\text{AlCl}_3\text{Bu})_2$ obtained with THF solution using a gold working electrode. The peak at -1V is due to the deposition of magnesium metal, and the peak at around 0.9V is attributed to the subsequent electrochemical dissolution of the magnesium metal. The electrochemical window obtained with this system exceeds 2.6V. It is clearly evident from the cyclic voltammogram that the process of magnesium deposition and dissolution is fully reversible.

- The potentiodynamic response of $\text{Mg}(\text{AlCl}_2\text{BuEt})_2$ in THF solution is given in FIG. 1b. The electrochemical window spans over 2.3 V, with a magnesium deposition peak starting at -0.3V (vs. Mg/Mg^+) with subsequent magnesium redissolution peak occurring at 0.4V. As in the previous case, it is evident from the cyclic voltammogram that the process of magnesium deposition and dissolution is fully reversible.

- 25 The above-mentioned results compare favorably with the results obtained with the electrolytes suggested by U.S. Patent No. 4,894,302 to Hoffman et al. The electrochemical window obtained with the prior art organo-borane salts, measured in a comparative study using magnesium dibutyl-diphenyl boronate ($\text{Mg}(\text{BBu}_2\text{Ph}_2)_2$), spans only about 1.8-1.9V. The wider electrochemical window obtained using electrolytes according to the
- 30

present invention indicates improved stability for the electrolytic solution and allows the use of more energetic cathode materials, such that both the cycle life and the energy density of the battery are substantially increased.

The SEM micrographs provided in FIG. 2 show different types of magnesium deposition patterns for electrolytes and electrochemical cells according to the present invention. FIGS. 2a-2b correspond to the electrochemical cell, described above, in which the electrolyte is $\text{Mg}(\text{AlCl}_3\text{Bu})_2$ in THF solution; FIG. 2c-2d correspond to the electrochemical cell, described above, in which the electrolyte is $\text{Mg}(\text{AlCl}_2\text{BuEt})_2$ in THF solution. With $\text{Mg}(\text{AlCl}_3\text{Bu})_2$, a wider electrochemical window is obtained relative to $\text{Mg}(\text{AlCl}_2\text{BuEt})_2$. However, the magnesium is deposited as spheres or as spherical clusters. In the case of the $\text{Mg}(\text{AlCl}_2\text{BuEt})_2$, the salt provides an electrochemical window that is somewhat more narrow, but the magnesium metal deposition is considerably more homogeneous, such that cyclability is greatly enhanced. Both electrolytes display superior electrochemical properties relative to electrolytes according to prior art.

In conjunction with the SEM microscopy, elemental analysis was performed by EDAX (energy dispersive analysis by x-ray fluorescence). The elemental analysis confirmed that the deposition of magnesium metal was substantially pure.

EXAMPLE 3

An electrochemical cell was prepared consisting of a Chevrel-phase cathode, a magnesium metal anode, and an electrolyte containing $\text{Mg}(\text{AlCl}_2\text{BuEt})_2$ salt in THF. The 25.7 mg cathode was made from a mixture of copper-leached Chevrel-phase material containing 10 weight-% carbon black and 10 weight-% PVDF as a binder, spread on stainless steel mesh. The solution was prepared from 0.25 Molar $\text{Mg}(\text{AlCl}_2\text{BuEt})_2$ salt in THF. The anode was a disc of pure magnesium metal, with a diameter of 16 mm and a thickness of 0.2 mm. The battery was encased in a stainless steel "coin cell" configuration with a paper separator made from glass fibers. The cell was

cycled on a standard charger-discharger with a current density of 23.3 milliamperes/gram. The potential limits for the cycling were between 0.5V at the fully discharged state and 1.8V for the fully charged state.

5 The battery was subjected to continuous cycling over 3 months. The excellent cyclability of the battery is clearly evident from FIG. 3, in which the cycles 340-345 are plotted next to the first five cycles (cycles 1-5). The battery performance remains strong over the entire length of the experiment. The charge density obtained in each discharge is 61 mAh per gram of the cathode material.

10

EXAMPLE 4

An electrolyte according to the present invention was prepared as follows: commercial, reagent-grade MgBu_2 , was dissolved in heptane. Commercial, reagent-grade AlEtCl_2 was added drop wise to the MgBu_2 solution according to the molar ratio. The mixture was stirred for 48 hours under an inert gas, and $\text{Mg}(\text{Bu}_2\text{AlCl}_2)_3$ was crystallized out of solution. The solvent was removed by evacuation. Ether solvents were added very slowly to the organomagnesium salt to produce a saturated solution (around 0.5M).

15 The ionic conductivity of the saturated $\text{Mg}(\text{Bu}_2\text{AlCl}_2)_3$ solution was $6.9 \times 10^{-3} \text{ Scm}^{-1} \text{ mol}^{-1}$ at 100kHz in a parallel cell configuration.

20 It will be appreciated that the above descriptions are intended only to serve as examples, and that many other embodiments are possible within the spirit and the scope of the present invention.

WHAT IS CLAIMED IS:

1. A non-aqueous electrolyte for use in an electrochemical cell, said electrolyte comprising:

- (a) at least one organic solvent and
- (b) at least one electrolytically active salt represented by the formula:



in which:

M' is selected from a group consisting of magnesium, calcium, aluminum, lithium and sodium;

Z is selected from a group consisting of aluminum, boron, phosphorus, antimony and arsenic;

R represents radicals selected from the following groups: alkyl, alkenyl, aryl, phenyl, benzyl, and amido;

X is a halogen (I, Br, Cl, F);

m = 1-3;

n = 0-5 and q = 6 for Z = phosphorus and arsenic, and

n = 0-3 and q = 4 for Z = aluminum and boron.

2. The non-aqueous electrolyte of claim 1, wherein M' is selected from a group consisting of magnesium, calcium, and aluminum.

3. The non-aqueous electrolyte of claim 1, wherein Z is aluminum.

4. The non-aqueous electrolyte of claim 1, wherein M' is selected from a group consisting of magnesium and calcium, and wherein Z is aluminum.

5. The non-aqueous electrolyte of claim 1, wherein M' is selected from a group consisting of magnesium and calcium, Z is aluminum, R and R'

are alkyl radicals, m is 2, and n is 1.

6. The non-aqueous electrolyte of claim 1, wherein M' is magnesium, Z is aluminum, R and R' are alkyl radicals, m is 2, and n is 1.

7. The non-aqueous electrolyte of claim 1, wherein the organic solvent contains THF, M' is magnesium, Z is aluminum, R and R' are alkyl radicals, m is 2, and n is 1.

8. The non-aqueous electrolyte of claim 1, wherein the electrolytically active salt is $\text{Mg}[\text{BuAlCl}_3]_2$.

9. An electrochemical cell comprising:

- (a) a metal anode;
- (b) an intercalation cathode; and
- (c) a non-aqueous electrolyte comprising:

0 at least one organic solvent and

1 at least one electrolytically active salt represented by the

formula:



in which:

M' is selected from a group consisting of magnesium, calcium, aluminum, lithium and sodium;

Z is selected from a group consisting of aluminum, boron, phosphorus, antimony and arsenic;

R represents radicals selected from the following groups: alkyl, alkenyl, aryl, phenyl, benzyl, and amido;

X is a halogen (I, Br, Cl, F);

m = 1-3;

n = 0-5 and q = 6 for Z = phosphorus, antimony and arsenic, and

$n = 0-3$ and $q = 4$ for $Z =$ aluminum and boron.

10. The electrochemical cell of claim 9, wherein M' in said electrolyte is selected from a group consisting of magnesium and calcium, Z is aluminum, R and R' are alkyl radicals, m is 2, and n is 1.

11. The electrochemical cell of claim 9, wherein said intercalation cathode is a Chevrel-phase intercalation cathode.

12. The electrochemical cell of claim 11, wherein said Chevrel-phase intercalation cathode is represented by the formula



wherein $x = 0 - 1$ and $y = 0 - 2$.

13. The electrochemical cell of claim 9, wherein said metal anode is magnesium.

14. The electrochemical cell of claim 9, wherein said metal anode is lithium.

1/2



Fig. 1A (Al-C13-Bu)₂-MgFig. 1B (Al-C12-Et-Bu)₂-Mg

Fig. 2A DEPOSITION




Fig. 2C DEPOSITION




Fig. 2B ZOOM






Fig. 2D ZOOM



SUBSTITUTE SHEET (RULE 26)



Cycle number

Fig. 3

INTERNATIONAL SEARCH REPORT

International application No.

PCT/US00/28683

A. CLASSIFICATION OF SUBJECT MATTER

IPC(7) : H01M 06/04, 10/26, 06/18, 04/58, 04/36, 04/58, 04/88; C01G 37/14

US CL : Please See Extra Sheet.

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

U.S. : 429/324, 199, 206, 207, 306, 319, 321, 322, 323, 218.1, 220, 231.5; 423/61; 252/182.1

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

WEST, EAST

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X ----- Y	US 5,491,039 A (SHACKLE) 2 February 1996, col. 3, lines 23-45; col. 7, lines 8-32.	1-10 and 13-14 ----- 11
X ----- Y	US 4,894,302 A (HOFFMAN et al) 16 January 1990, col. 4, lines 18-65; col. 5, lines 45-50; col 4, lines 52-60.	1-10 and 13-14 ----- 11
Y	US 4,139,681 A (KLEMMANN et al) 13 February 1979, abstract.	1, 3, 9, 13-14
Y	US 4,104,450 A (WHITNEY et al) 1 August 1978, col. 2, line 48 to col. 3, line 32.	1, 3, 9, 14
Y	US 4,917,871 A (DAHN et al) 17 April 1990, abstract.	11

☒ Further documents are listed in the continuation of Box C. ☐ See patent family annex.

* Special categories of cited documents:	"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
"A" document defining the general state of the art which is not considered to be of particular relevance	"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
"E" earlier document published on or after the international filing date	"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	"&" document member of the same patent family
"O" document referring to an oral disclosure, use, exhibition or other means	
"P" document published prior to the international filing date but later than the priority date claimed	

Date of the actual completion of the international search

29 DECEMBER 2000

Date of mailing of the international search report

26 JAN 2001

Name and mailing address of the ISA/US
Commissioner of Patents and Trademarks
Box PCT
Washington, D.C. 20231

Facsimile No. (703) 305-3230

Authorized Officer

RAYMOND ALEJANDRO

Telephone No. (703) 308-0661

Form PCT/ISA/210 (second sheet) (July 1998)*

INTERNATIONAL SEARCH REPORT

International application No.
PCT/US00/28683

C (Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	JP 6-223818 (WAKIHARA et al) 12 August 1994, abstract.	11
Y	JP 5-343065 (SUZUKI et al) 24 December 1993, abstract.	11
A	US 4,104,451 A (KLEMMANN et al) 1 August 1978.	1, 3, 9, 14.
A	US 4,542,081 A (ARMAND et al) 17 September 1985.	1, 3, 9, 14
A	US 5,849,432 A (ANGELL et al) 15 December 1998.	1-14

Form PCT/ISA/210 (continuation of second sheet) (July 1998)*

INTERNATIONAL SEARCH REPORT

International application No.
PCT/US00/28683

A. CLASSIFICATION OF SUBJECT MATTER:

US CL :

429/324, 199, 206, 207, 306, 319, 321, 322, 323, 218.1, 220, 231.5; 423/61; 252/182.1

Form PCT/ISA/210 (extra sheet) (July 1998)*

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ BLACK BORDERS
- ☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☐ FADED TEXT OR DRAWING
- ☐ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☐ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☒ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☐ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☐ OTHER: _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.